Catalytic Pyrolysis of Palm Empty Fruit Bunch over Activated Natural Dolomite Catalyst: Product Distribution and Product Analysis

Arif Hidayat^{1,a*}, Muflih Arisa Adnan^{1,b} and Achmad Chafidz Mas Sahid^{1,c}

¹Chemical Engineering Department, Universitas Islam Indonesia, Indonesia ^aarif.hidayat@uii.ac.id, ^bmuflih.adnan@uii.ac.id, ^cachmad.chafidz@uii.ac.id *arif.hidayat@uii.ac.id

Keywords: bio-oil, dolomite, palm empty fruit bunches, catalytic pyrolysis, product distribution.

Abstract. In this study, an activated natural dolomite catalyst is used as catalyst for the palm empty fruit bunches (PEFB) pyrolysis to produce bio-oil. The research was conducted in fixed bed reactors operating in batches by varying several parameters, which are temperature (400-600°C) and nitrogen gas flow rate (100-300 mL.min⁻¹). The results show that the catalytic pyrolysis process using an activated natural dolomite catalyst obtains a maximum liquid yield of 35.87% when using a 500°C catalytic pyrolysis temperature and the rate of nitrogen gas is 100 cm³/minute, while the yield of gas and solids is 53.12% and 11.76%, respectively. The use of the dolomite activation catalyst influences the product distribution of pyrolysis and the bio-oil chemical compounds.

Introduction

The transportation sector contributes 94% of the total global demand for fuel. On the other hand, the demand for biofuels is gradually increasing significantly to reduce dependence on fossil fuels, government policies, and the availability of abundant raw materials and awareness of environmental preservation. Biofuel has various advantages compared to fossil fuels, including renewable, low greenhouse gas emissions, and sustainable. In last few decades, biomass has gain much pay attention from researchers as the main raw material for producing biofuels in order to overcome various problems of energy supply and environmental protection due to the impact of the use of fossil fuels [1]. Biomass is consists of lignocellulosic material, with the main components being cellulose, hemicellulose, and lignin.

Indonesia is the largest producer of palm oil in the world since 2008. The processing of palm oil fresh fruit bunches to produce Crude Palm Oil (CPO) will generate Palm Empty Fruit Bunch (PEFB) as a solid waste [2]. From each processing of 1 ton of EFB, the resulting solid waste is 144 kg of 64 kg mesocarp fiber shells and 210 kg of oil palm empty fruit bunches (PEFB) [3]. Indonesia's CPO production in 2017 reached 42 million tons and in 2018 it is estimated to reach 45 million tons. This number will continue to increase with the increase in Indonesia's FFB production. Thus, biomass solid waste generated will be more and more and need to be addressed so as not to cause environmental pollution. Biomass from palm byproducts can be used as a source of renewable energy.

Pyrolysis is one of the most promising technologies for the biomass conversion into bio-oil, biochar and gas products through thermochemical process [4] Bio-oil is obtained from biomass pyrolysis at a temperature range of 350 to 600°C in the absence of oxygen during the process. Bio-oil is an organic liquid that is dark brown in color and has high viscosity [5]. The bio-oil chemical composition is composed of several different chemicals, such as aldehydes, esters, acids, alcohols, phenols, ketones, aromatics, and oligomers. The compounds contributes to the properties of bio-oil. Bio-oil has a low heating value because it contains water of 15-30% by mass; oxygen compound 35-50% by mass; and high acidity in the range of 2-3 pH values. The properties of bio-oil including density, viscosity, acidity, compound content, acidity, and heating value can be significantly improved by upgrading process.

Biomass is decomposed into gas bio-oil, and bio-char products through pyrolysis in the temperature range of 400-600°C in an inert environment. The use of fixed bed reactors for pyrolysis

has been used in several studies. During the pyrolysis process, the devolatilization of the biomass structure becomes steam which is then condensed into bio-oil. Oxygenate compounds, such as phenols, ketones, furans, acids, and anhydrosugars are the result of the breakdown of lignin and cellulose which are the main components of biomass. Oxygenate compounds contribute to several undesirable properties in bio-oil, such as low heating value, high acidity, corrosiveness, instability, and. Therefore, the bio-oil quality could be improved by reducing the content of oxygenate compounds through deoxygenation and cracking reactions with the help of catalysts. The deoxygenation process is carried out through the stages of dehydration, decarboxylation, and decarbonylation. Several metal oxide catalysts, such as ZnO [6], MgO [7], CaO [7], ZrO₂ [8], TiO₂ [9], SiO₂ [10], Al₂O₃ [11], and others have been studied to improve the quality of bio-oil through the catalytic pyrolysis process. The catalytic pyrolysis process is a promising method because it provides many advantages, including the absence of hydrogen consumption and the process conditions at atmospheric pressure.

Dolomite is an abundant and inexpensive natural mineral ingredient. Dolomite contains metal oxides in the form of Calcium Oxide (CaO) and Magnesium Oxide (MgO). The application of dolomite as a catalyst has received great attention, especially for the process of gasification of biomass at high temperatures to reduce the formation of tar. Reducing the formation of tar is accomplished by various stages, namely cracking of vapors formed, reforming compounds with high molecular weight, and improving yield and quality of synthetic gases. Moreover, dolomite can also be utilized as a catalyst to increase the quality of bio-oil by cracking heavier organic matter into lighter fractions and reducing the oxygenate compounds formed. Berrueco et al. [2014] use dolomite as a catalyst to reduce tar yield by 51%, in the gasification process of cypress trees carried out at a temperature of 750°C [12]. Yu et al. [2009] have also learned that tar conversion of 65-75% can be achieved when using a dolomite catalyst at a reaction temperature of 700°C [13].

In this research, natural dolomite is used as a catalyst for the PEFB catalytic pyrolysis process to increase bio-oil properties. The research was conducted in fixed bed reactors operating in batches by varying several parameters, which are temperature (400-600°C) and nitrogen gas flow rate (100-300 mL.min-1).

Experimental

Materials. Palm Empty Fruit Bunches (PEFB) were obtained from oil palm plantations in the Pangkalan Bun area, South Kalimantan Province, Indonesia. Before the pyrolysis process, PEFB is dried in the sun and cut into small sizes and the drying process is continued in an oven at 105°C for a day and night. PEFB was then ground and sieved to a size between 50–100 mesh. Moisture content from dry PEFB is measured to ensure that the water content is less than 10% by mass.

Catalyst Preparation. Natural dolomite which will be used for the catalytic pyrolysis process was obtained from Klaten Regency, Central Java Province, Indonesia with a particle size of 60-80 mesh (180-250 µm). Before being used as a catalyst, natural dolomite was calcined at 900°C for 3 hours. During the calcination process, carbonates are broken down into CaO and MgO. he results of the measurement of the specific surface area of the activation dolomite catalyst using the Brunauer-Emmett-Teller (BET) equation were obtained at 10.58 m²/g. Crystallography of the activated dolomite catalyst structure was identified using an X-Ray Diffractometer (XRD) with a CuK α radiation source and operated at a scanning speed of 5 °/min from 5 to 80°. Figure 1 shows the XRD diffraction pattern of natural dolomite and dolomite catalyst activation. The diffraction pattern of natural dolomite shows an intense peak at 20= 30.8; 33.5; 35.5 and 37.4° corresponding to CaMg (CO₃)₂, the other peak at 20 = 41.3°; 50.6°; and 51.2° indicate CaO₂ compatibility. Furthermore, the activated dolomite XRD pattern showed diffraction peaks associated with the presence of CaO (20 = 32.6°; 37.5°; 54.2°; and 67.4°) and MgO (20 = 43.3° and 74.8°).



Fig. 1. XRD patterns of (a) natural dolomite; and (b) activated dolomite

Catalytic Pyrolysis Experiments. Pyrolysis experiments are carried out in a fixed bed reactor made of stainless steel which are operated below at atmospheric pressure. The reactor is placed into a cylindrical furnace that is electrically heated. The furnace is equipped with a thermocouple to monitor temperature and is controlled by a temperature controller. At first 10 grams of PEFB are placed inside the reactor. Before the temperature is raised, Nitrogen (N₂) gas is flowed into the reactor to remove oxygen. Then, the furnace is raised at a temperature of 10°C/min to reach 400°C. The temperature is kept stable for 2 hours and during heating, N₂ gas flows into the reactor at a rate of 100 mL/min. The gases formed from pyrolysis flow out together with N₂ gas from the top of the reactor. The gas passes through a condenser which functions to condense the gas. Liquid products or bio-oil condensation from condensers are collected in Erlenmeyer flasks and their recovery is measured. Experiments carried out by doing variations on various parameters, namely temperature (400-600°C), the ratio of the mass of biomass to the catalyst (0.5-2.0), and the flow rate of nitrogen gas (100-300 cm³.min⁻¹). Bio-oil obtained under experimental conditions that provide maximum oil yields is characterized by physical and chemical properties. The chemical composition of bio-oil is analyzed using gas chromatography-mass spectrometry (GC-MS).



Fig. 2. Catalytic Pyrolysis Experiments Apparatus

Results and Discussion

Effect of Pyrolysis Method. Fig. 3 shows the comparison of the product distribution on pyrolysis using activated dolomite as a catalyst and the non-catalyzed process for PEFB pyrolysis with the same operating conditions i.e., nitrogen gas flow rate of 200 mL/min, pyrolysis temperature 600°C as non-catalytic pyrolysis. The percentage of gas obtained is determined by the difference between the number of feed samples with the amount of liquid and charcoal products obtained. The use of activated dolomite catalysts gives a higher percentage of gas products compared to the results of non-catalytic process show a greater percentage compared to pyrolysis using activated dolomite catalysts.



Fig. 3. Effect of Pyrolysis Type on the Product Distribution

Effect of Temperature. To study the effect of temperature on the results of the distribution of PEFB catalytic pyrolysis products with dolomite catalysts the activation of the experiment was carried out by varying the temperature of 400, 500 and 600°C at a constant flow rate of nitrogen gas at 200 mL/min and the ratio of mass of biomass to catalyst 1.0. The distribution of PEFB catalytic pyrolysis products with temperature variations is shown in Fig. 4. Char acquisition decreases with an increase in temperature from 400 to 600°C. Decreased char acquisition is caused by PEFB decomposition and secondary decomposition of residual charcoal due to increasing temperatures. The acquisition of bio-oil and gas has increased with all the high temperatures as shown in Fig. 4. This is related to the secondary decomposition activity of volatile products formed by pyrolysis. The acquisition of a slightly higher gas product is likely due to a water gas shift reaction from pyrolysis catalyzed by activation dolomite.



Fig. 4. Effect of Temperature on the Product Distribution of PEFB Catalytic Pyrolysis

Effect of Nitrogen Gas Flow Rate. The effect of nitrogen gas flow rate on the distribution of PEFB pyrolysis products was observed by varying the magnitude of the N2 flow rate at values of 100, 200 and 300 mL/min with the catalytic pyrolysis temperature maintained stable at 600°C. The results of the influence of nitrogen gas flow rate on the distribution of PEFB pyrolysis products are shown in Fig. 5. Gas yield decreases slightly when the nitrogen gas flow is increased from 100 to 200 mL/min and then increases with a further increase in flow rate to 300 mL/min. The bio-oil yield is different from the results obtained from the gas yield. At a nitrogen gas flow rate of 200 mL/min, the highest bio-oil product results are obtained. This indicates that the flow rate can increase the activity of activated dolomite catalyst during the pyrolysis process.



Fig. 5. Effect of Nitrogen Gas Flow Rate on the Product Distribution of PEFB Catalytic Pyrolysis

The GC–MS Analysis of the Bio-oil. Bio-oil characterization using gas chromatography-mass spectrometry (GC-MS) was carried out to determine the content of complex and heterogeneous compounds. The classification of the distribution of major vegetable oil product compounds in PEFB pyrolysis and catalytic pyrolysis can be seen in Fig. 6. Bio-oil from non-catalytic and catalytic pyrolysis contains several hydrocarbon compounds (acids, alcohols, aldehydes, ketones, and esters), aromatics, and oxygenates. The use of dolomite catalyst can increase the productivity of aliphatic hydrocarbon compounds (alkanes and alkenes), esters and alcohols. On the other hand, the amount of acid and alcohol content decreases when the dolomite catalyst is activated. However, the content of aromatic compounds in the form of phenols has increased slightly.



Fig. 6. Classification of major bio-oil product compound distribution in pyrolysis and catalytic pyrolysis of PEFB

Conclusions

In this study, the catalytic pyrolysis experiments of PEFB were conducted in a fix-bed reactor over the Activated Dolomite catalyst. The research was conducted in fixed bed reactors operating in batches by varying several parameters, which are temperature (400-600°C) and nitrogen gas flow rate (100-300 mL.min⁻¹). The optimal yield of bio-oil could be achieved at the pyrolysis temperature of 500 °C. Higher nitrogen flow rates were more favorable for the production of the bio-oil. The GC–MS analysis shows the use of dolomite catalyst can increase the content of esters, keton, aldehyde, alcohols and phenolic compounds in the bio-oil.

Acknowledgment

The authors would like to acknowledge to Directorate General of Higher Educations of Indonesia, Kemenristekdikti for financial support through the research grant of Penelitian Desentralisasi 2019.

References

- [1] N. Abdullah, H. Gerhauser, Bio-oil derived from empty fruit bunches, Fuel 87 (2008) 2606-2613.
- [2] C. Berrueco, D. Montané, B. Matas Güell, G. del Alamo, Effect of temperature and dolomite on tar formation during gasification of torrefied biomass in a pressurized fluidized bed, Energy 66 (2014) 849-859.
- [3] T. Kan, V. Strezov, T.J. Evans, Lignocellulosic biomass pyrolysis: A review of product properties and effects of pyrolysis parameters, Renewable and Sustainable Energy Reviews 57 (2016) 1126-1140.
- [4] C. Liu, H. Wang, A.M. Karim, J. Sun, Y. Wang, Catalytic fast pyrolysis of lignocellulosic biomass, Chemical Society Reviews 43 (2014) 7594-7623.
- [5] T. Mochizuki, D. Atong, S.-Y. Chen, M. Toba, Y. Yoshimura, Effect of SiO2 pore size on catalytic fast pyrolysis of Jatropha residues by using pyrolyzer-GC/MS, Catalysis Communications 36 (2013) 1-4.
- [6] V. Nair, R. Vinu, Production of guaiacols via catalytic fast pyrolysis of alkali lignin using titania, zirconia and ceria, Journal of Analytical and Applied Pyrolysis 119 (2016) 31-39.
- [7] N.M.N. Qadi, A. Hidayat, F. Takahashi, K. Yoshikawa, Co-gasification kinetics of coal char and algae char under CO2 atmosphere, Biofuels 8 (2017) 281-289.
- [8] L. Santamaria, A. Arregi, J. Alvarez, M. Artetxe, M. Amutio, G. Lopez, J. Bilbao, M. Olazar, Performance of a Ni/ZrO2 catalyst in the steam reforming of the volatiles derived from biomass pyrolysis, Journal of Analytical and Applied Pyrolysis 136 (2018) 222-231.
- [9] B. Sutrisno, A. Hidayat, Pyrolysis of palm empty fruit bunch: Yields and analysis of bio-oil, MATEC Web Conf. 154 (2018).
- [10] T. Yoshizaki, Y. Shirai, M.A. Hassan, A.S. Baharuddin, N.M. Raja Abdullah, A. Sulaiman, Z. Busu, Improved economic viability of integrated biogas energy and compost production for sustainable palm oil mill management, Journal of Cleaner Production 44 (2013) 1-7.
- [11] Q.Z. Yu, C. Brage, T. Nordgreen, K. Sjöström, Effects of Chinese dolomites on tar cracking in gasification of birch, Fuel 88 (2009) 1922-1926.
- [12] X. Zhao, M. Wang, H. Liu, C. Zhao, C. Ma, Z. Song, Effect of temperature and additives on the yields of products and microwave pyrolysis behaviors of wheat straw, Journal of Analytical and Applied Pyrolysis 100 (2013) 49-55.
- [13] Y. Zhou, Z. Chen, H. Gong, L. Chen, H. Yu, W. Wu, Characteristics of dehydration during rice husk pyrolysis and catalytic mechanism of dehydration reaction with NiO/γ-Al2O3 as catalyst, Fuel 245 (2019) 131-138.



0 items

Search
Journals
Engineering Research
Advanced Engineering Forum
Applied Mechanics and Materials
Engineering Chemistry
Engineering Innovations
Journal of Biomimetics, Biomaterials and Biomedical Engineering
International Journal of Engineering Research in Africa
Materials Science
Advanced Materials Research
Defect and Diffusion Forum
Diffusion Foundations and Materials Applications
Journal of Metastable and Nanocrystalline Materials
Journal of Nano Research
Key Engineering Materials
Materials Science Forum

Nano Hybrids and Composites
Solid State Phenomena
Engineering Series
Advances in Science and Technology
Construction Technologies and Architecture
Books
Special Book Collections
Foundations of Materials Science and Engineering
Scientific Books Collection
Specialized Collections
Retrospective Collection

Materials Science Forum

ISSN: 1662-9752

Details

Volumes

Editorial Board

Enter Number of Volume

Year

1	2	3	4	5	 >	>>

Volumes

Materials Science Forum Vol. 1081

Edited by: Dr. Thangaprakash Sengodan, Dr. Peter Horňak, Dr. Miloš Matvija, Dr. Denis B. Solovev and Ramadhansyah Putra Jaya

Online since: March 2023

Description: This special topic edition is devoted to current issues in materials science and materials synthesis and processing technologies. The publication will be useful to materials <u>...more</u>

Materials Science Forum Vol. 1080

Edited by: Dr. Juniastel Rajagukguk, Prof. Agustinus Agung Nugroho, Prof. Shixuan Xin, Prof. Iulian Antoniac and Prof. Guillermo Requena

Online since: January 2023

Description: This special edition is dedicated to analysing properties and possible methods of treatment and applications of the comprehensive nomenclature of modern special and <u>...more</u>

Materials Science Forum Vol. 1079

Edited by: Prof. Iulian Antoniac, Prof. Guillermo Requena, Dr. Xinyu Hu, Dr. Omar S. Dahham and Dr. Nur Hidayati Othman

Online since: December 2022

Description: This edition presents a series of research results in materials science and technologies of materials synthesis and processing used in many branches of modern

<u>...more</u>

Materials Science Forum Vol. 1078

Edited by: Prof. Iulian Antoniac, Prof. Guillermo Requena, Dr. Omar S. Dahham and Dr. Xinyu Hu

Online since: December 2022

Description: This special topic edition presents the latest research results in materials science and materials synthesis and processing technologies for various branches of modern ...more

Materials Science Forum Vol. 1077

Edited by: Dr. Omar S. Dahham, Assoc. Prof. Dr. Norzahir Sapawe, Dr. Noor Faizah Che Harun and Prof. Mosbeh Kaloop

Online since: December 2022

Description:

This edition presents the latest research results in materials science and technologies for <u>...more</u>

https://www.scientific.net/MSF

Materials Science Forum Vol. 1076

Edited by: Assoc. Prof. Dr. Norzahir Sapawe, Dr. Noor Faizah Che Harun, Prof. Takahiro Ohashi, Prof. Chafic-Touma Salame and Prof. Yuyuan Zhao

Online since: December 2022

Description: This edition acquaints readers with the latest scientific and engineering research in materials properties and methods of their applications, as well as the results of developing ...more

Materials Science Forum Vol. 1075

Edited by: Prof. Yuyuan Zhao, Prof. Omar S. Es-Said, Dr. G. Kumaresan, Dr. N. Siva Shanmugam and Dr. V. Dhinakaran

Online since: November 2022

Description: The latest research results in the area of materials science and applied technologies and methods of materials synthesis and processing are described in this ...more

Materials Science Forum Vol. 1074

Edited by: Dr. Ramya Muthusamy, Dr. Thangaprakash Sengodan and Prof. long Wan Hu

Online since: November 2022

Description: In this edition, the reader can get acquainted with the research results of properties for structural and functional materials, and materials and technologies in

...more

Materials Science Forum Vol. 1073

Edited by: Prof. Jong Wan Hu, Dr. Ramya Muthusamy and Dr. Thangaprakash Sengodan Online since: October 2022 **Description:**

In this edition, the research results of properties for structural and functional materials, ...more

Materials Science Forum Vol. 1072

Edited by: Prof. Yafang Han, Dr. Fenfen Liang, Prof. Ke Yong Shao, Dr. Ramya Muthusamy and Dr. Thangaprakash Sengodan Online since: October 2022

Description:

This issue presents to the reader's attention the research results in the sphere of structural ...more

DISTRIBUTION & ACCESS

FOR PUBLICATION

INSIGHTS

DOWNLOADS

ABOUT US

POLICY & ETHICS

CONTACT US

IMPRINT

PRIVACY POLICY

SITEMAP

ALL CONFERENCES

ALL SPECIAL ISSUES

ALL NEWS

Scientific.Net is a registered brand of Trans Tech Publications Ltd \odot 2023 by Trans Tech Publications Ltd. All Rights Reserved

Table of Contents

Preface

Chapter 1: Metallurgical Technologies, Properties of Steels and Alloys

Microstructure and Impact Toughness of Flux-Cored Arc Welded SM570-TMC Steel at Low and High Heat Input	
H. Oktadinata, W. Winarto and E.S. Siradj	3
Investigation of the Intermetallic Formation on Wet Underwater Welding of AISI 4012 Steel	
A.D. Anggono, Suwantri, W.A. Siswanto and J. Sedyono	10
Effect of Magnesium on the Strength, Stiffness and Toughness of Nodular Cast Iron A.S. Darmawan, P.I. Purboputro, A. Yulianto, A.D. Anggono, Wijianto, Masyrukan, R.D. Setiawan and N.D. Kartika	17
Effect of Ti Contents on the Microstructure and Mechanical Properties of NiAlTi System D. Wicaksono, X.M. Zhu, M.S. Mustapa, S. Yulianto, A.Y. Nasution and T.W.B. Riyadi	24
Defect Investigation of Sand Casted Aluminum Cooling Fan D. Prihtiantoro, A.D. Anggono and W.A. Siswanto	30
Microstructure and Hardness of Gray Cast Iron as a Product of Solidification in Permanent	
A. Yulianto, R. Soenoko, W. Suprapto, A. Sonief, A.S. Darmawan and M.D. Setiawan	37
Structure and Properties of NiAlTi Systems Formed by Combustion Synthesis T.W.B. Riyadi	44
Chapter 2: Characterization and Testing of Materials	
HAp Coated Hip Prosthesis Contact Pressure Prediction Using FEM Analysis M. Nagentrau, A.L. Mohd Tobi, S. Jamian and Y. Otsuka	53
Effect of the Fine Recycled Aggregates on the Dynamic Compressive Behavior of Recycled	
S. Ismail, M.A. Abd Hamid and Z. Yaacob	62
Assessment of the Stress-Strain State of a Tube Sheet of the Heat Exchanger at Rotary Friction Welding Application	
A.S. Tokarev, D. Karetnikov, R.G. Rizvanov, A.M. Fahrushin and M.Z. Zaripov	70
Characterisation of Electrode Drying Effect on the Tungsten Carbide Hardfacing	
Microstructure M. Nagentrau, A.L. Mohd Tobi, S. Jamian and M. Sambu	77
Fatigue Behavior Improvement of A356 Aluminum Alloy of Motorcycle Cast Wheel Produced by High Speed Centrifugal Casting Based on T6 Heat Treatment and Artificial	
P.T. Iswanto, Akhyar, A. Janata, L.M. Mauludin and H.M. Sadida	86
Electrochemical Performance of Barium Strontium Cobalt Ferrite -Samarium Doped Ceria- Argentum for Low Temperature Solid Oxide Fuel Cell	
U.A. Yusop, T.K. Huai, H.A. Rahman, N.A. Baharuddin and J. Rahario	94

Resistance to Chloride Penetration of Recycled Aggregate Concrete Modified Using Treated Coarse Recycled Concrete Aggregate and Fibres S. Ismail and M. Ramli 101

Chapter 3: Technologies of Biomass Processing

Catalytic Pyrolysis of Palm Empty Fruit Bunch over Activated Natural Dolomite Catalyst: Product Distribution and Product Analysis A. Hidayat, M.A. Adnan and A. Chafidz

CaO/Natural Dolomite as a Heterogeneous Catalyst for Biodiesel Production B. Sutrisno, A.D. Nafiah, I.S. Fauziah, W. Kurniawan, H. Hinode and A. Hidayat	117
Investigating the Potential Use of Cassava Leaf Extract as a Natural Coloring Substance for Fabrics	
S. Rusdi, M.Y. Zakaria, R.N.F. Aditya and A. Chafidz	123
Investigating the Potential Use of Papaya Leaf Extract as Natural Dyes in the Textile Industry	
S. Rusdi, H.F. Maulana, N.L. Samudro and A. Chafidz	129
Synthesis of Grafted Cationic Starch with DMDAAC Using Ammonium Persulfate/Carbamide Initiation System H. Tang, P.Y. Zhang, T.X. Li and Y. Ma	135
Biodiesel Synthesis from Used Cooking Oil Using Red Mud as Heterogeneous Catalyst A. Hidayat, G.K. Roziq, F. Muhammad, W. Kurniawan and H. Hinode	144
Effect of HCl-Alcoholic Treatment on the Modification of Jackfruit (Artocarpus	
<i>heterophyllus</i> Lam) Seed Starch T.H.T. Le, H.T. Nguyen, V.K. Nguyen, T.L. Nguyen and T.T. Nguyen	150
Chapter 4: Technologies of Chemical Production and Wastewater Treatment	
Characterization of Hydroxyapatite Synthesized from Calcium Hydroxide and Phosphoric Acid as Adsorbents of Lead in Wastewater H.T. Nguyen and P.T. Dang	159
Research and Application of a New Demulsifier for the Processing of Produced Liquid in Chanqing Gasfield	177
S.J. Chen, F. Tang, W. Han, Q.n. LIU and G. Chen Utilization of Modified Zeolite Materials as Chromium Cation Exchanger for Treatment of Liquid Waste from Electroplating Industries	100
Z. Salimin, M. Susianto, B. Batara and A. Chafidz	172
Chemical Treatment of Liquid Waste Generated from Leather Tannery Industry by Using Alum as Coagulant Material	
Z. Salimin, F.W. Satiyoaji, D.A. Prasetya and A. Chafidz	178
Synthesis of Hydrophobically Associating Polymers and the Application as Oil-Displacing Agent R I Zhang II. Zhao, X K. Wang, Z P. Zhou and G. Chen	185
Corrosion Rate Analysis of API 51, Gr B Steel Pine in Acetic Acid Contained Crude Oil	100
Treatment System by Using Amine Base Organik Corrosion Inhibitor A. Swandito and V. Malau	191

0 items

Search
Journals
Engineering Research
Advanced Engineering Forum
Applied Mechanics and Materials
Engineering Chemistry
Engineering Innovations
Journal of Biomimetics, Biomaterials and Biomedical Engineering
International Journal of Engineering Research in Africa
Materials Science
Advanced Materials Research
Defect and Diffusion Forum
Diffusion Foundations and Materials Applications
Journal of Metastable and Nanocrystalline Materials
Journal of Nano Research
Key Engineering Materials
Materials Science Forum

Nano Hybrids and Composites
Solid State Phenomena
Engineering Series
Advances in Science and Technology
Construction Technologies and Architecture
Books
Special Book Collections
Foundations of Materials Science and Engineering
Scientific Books Collection
Specialized Collections
Retrospective Collection

Materials Science Forum - Editorial Board

ISSN: 1662-9752

Volumes	
Editorial Board	

Founding Editor

Fred H. Wohlbier

Honorary Editor

Prof. Graeme E. Murch

University of Newcastle, Centre for Mass and Thermal Transport in Engineering Materials, School of Engineering; Callaghan, Australia, NSW 2308;

Editor(s) in Chief

Prof. Iulian Antoniac

University Politehnica of Bucharest, Faculty of Materials Science and Engineering; 313 Splaiul Independentei, Bucharest, 060042, Romania;

Prof. Guillermo Requena

ORCID

German Aerospace Center (DLR), Institute of Materials Research ; Köln, DE-51170, Germany;

Editorial Board

Prof. Dezső L. Beke

University of Debrecen, Department for Solid State Physics; Bem tér 18/b, Debrecen, 4026, Hungary;

Prof. Giorgio Benedek

University of Milano Bicocca, Department of Materials Science; U5, Universitá di Milano-Bicocca, Via R. Cozzi 55, Milano, 20125, Italy;

Dr. Giacomo Benvenuti

<u>ORCID</u>

ABCD Technology; Switzerland;

Prof. Anil K. Bhatnagar

University of Hyderabad, School of Physics and School of Engineering; Hyderabad, India, 500046;

Prof. Chi Ming Chan

Hong Kong University of Science and Technology, Department of Chemical and Biomolecular Engineering, Clear Water Bay; Kowloon, China;

Dr. Abel S. Fenta

<u>ORCID</u>

CERN; Genève, CH-1211, Switzerland;

Roberto B. Figueiredo

Federal University of Minas Gerais, Department of Metallurgical and Materials Engineering; Belo Horizonte, MG, 30, Brazil, 31270-901;

Prof. Hermann G. Grimmeiss

Lund University, Department of Solid State Physics; Box 118, Lund, 221 00, Sweden;

Prof. Jerzy Jedlinski

AGH University of Science and Technology, Faculty of Materials Science and Ceramics, Department of Physical Chemistry and Modeling of Processes and Surface Engineering; al. Mickiewicza 30, Kraków, 30-059, Poland;

Prof. Megumi Kawasaki

ORCID

Oregon State University, School of Mechanical, Industrial and Manufacturing Engineering; 204 Rogers Hall, Corvallis, USA, 97331;

Prof. Terence G. Langdon

University of Southampton, Faculty of Engineering and the Environment; Lanchester Building (Bldg. 7), Highfield Campus, Southampton, United Kingdom, SO17 1BJ;

Prof. Jai Sung Lee

Hanyang University, Department of Metallurgy and Materials Science; 55 Daehak-no, Sangnok-gu, Ansan, Korea, South, 426-791;

Prof. Eric J. Mittemeijer

Max Planck Institute for Intelligent Systems; Heisenbergstrasse 3, Stuttgart, 70569, Germany;

Prof. Stephen J. Pearton

University of Florida, Department of Materials Science and Engineering; Gainesville, USA, 32611-6400;

Prof. Vassilis Pontikis

Commissariat à l'Energie Atomique et les Energies Alternatives (CEA), CEA-Saclay; Bdg. 524, Gif-sur-Yvette, 91191, France;

Prof. András Roósz

Hungarian Academy of Sciences, Miskolc University (HAS-MU); Miskolc-Egyetemváros, 3515, Hungary;

Prof. David N. Seidman

Northwestern University, Department Materials Science and Engineering; Cook Hall, 2220 Campus Drive, Evanston, USA, 60208;

Dr. Ching Hua Su

NASA/Marshall Space Flight Center, EM31 NASA/Marshall Space Flight Center; Huntsville, USA, 35812;

Prof. David Tomanek

Michigan State University, Physics and Astronomy Department; 567 Wilson Road, East Lansing, USA, MI 48824-6455;

Prof. A.S. Wronski

University of Bradford, School of Engineering, Design and Technology; West Yorkshire, Bradford, United Kingdom, BD7 1DP;

Emeritus Prof. David J. Young

University of New South Wales, School of Materials Science and Engineering; Sydney, Australia, NSW 2052;

DISTRIBUTION & ACCESS FOR PUBLICATION INSIGHTS DOWNLOADS ABOUT US POLICY & ETHICS CONTACT US IMPRINT PRIVACY POLICY SITEMAP ALL CONFERENCES ALL SPECIAL ISSUES

Scientific.Net is a registered brand of Trans Tech Publications Ltd © 2023 by Trans Tech Publications Ltd. All Rights Reserved



ICOAMS International Conference on Advanced Materials Science

ICOAMS2019

The 2nd International Conference on Advanced Materials Science (ICOAMS2019) 23-24 October 2019

LATEST NEWS: There are many request from authors, paper submission extended until 12 October 2019 To submit ICOAMS2019 papers, you have to follow the steps below:

STEP 1: Register your correct name and email to scientific.net. The correspondence will be via email.

First Name *	
Thist Name	
3/2 J J L N L	
Middle Name	
Last Name *	
Last Nume	
Emoil *	
Ellian	

CLICK HERE to Send Request

STEP 2: See your email. In less than 24 hours scientific.net will create an author account and notify you by email

STEP 3: After you have received the username and password, you can submit the paper in scientific.net

All accepted reviewed-papers will be published by Scienific.Net in Material Science Forum indexed by SCOPUS. Authors who submit to this conference agree to the Publication Ethics.



3/26/23, 10:15 AM



Assoc. Prof. Dr. Agus Dwi Anggono

Finite element analysis, Simulation, Design and Modeling, Manufacturing Universitas Muhammadiyah Surakarta (UMS) Indonesia

-

Mr. Agus Mujianto

Mechanical Enginering Materials Universitas Muhammadiyah Kalimantan Timur (UMKT) Indonesia



Mrs. Anis Siti Nurrohkayati

Industrial Engineering, Manufacture System Universitas Muhammadiyah Kalimantan Timur (UMKT) Indonesia



Mr. Ardiansyah Materials

Universitas Muhammadiyah Kalimantan Timur (UMKT) Indonesia



Mr. Binyamin Solid Mechanics, Materials, Finite Element, Energy Universitas Muhammadiyah Kalimantan Timur (UMKT) Indonesia



Dr. Dafit Feriyanto Advanced materials, manufacturing Universitas Mercu Buana (UMB) Indonesia



Mr. Hery Tri Waloyo Renewable Energy Universitas Muhammadiyah Kalimantan Timur (UMKT) **Indonesia**



Dr. Iis Siti Aisyah Metalurgy, Materials Universitas Muhammadiyah Malang (UMM) Indonesia



Dr. Joko Sedyono Composite Materials, Optimization, Manufacturing Process Universitas Muhammadiyah Surakarta (UMS) Indonesia



Dr. Kun Harismah Organic chemistry, organic synthesis, natural products Universitas Muhammadiyah Surakarta (UMS) Indonesia



٣,

Assoc. Prof. Dr. Marwan Effendy Computational heat, Computational fluid dynamics Universitaa Muhammadiyah Surakarta (UMS) Indonesia

Muhammad Syukron, Ph.D

3/26/23, 10:15 AM

Materials science Universitas Muhammadiyah Surakarta (UMS) Indonesia



Mr. Ngafwan

Nano materials Universitas Muhammadiyah Surakarta (UMS) Indonesia



Dr Prantasi Harmi Tjahjanti

Mechanical Engineering Universitas Muhammadiyah Sidoarjo (UMSIDA) Indonesia

٢,

Dr Purnomo

Fracture Mechanics Universitas Muhammadiyah Semarang Indonesia



Assoc. Prof. Dr. Sarjito

Computational Heat, Computational fluid dynamics Universitas Muhammadiyah Surakarta (UMS) Indonesia



Mr. Sigiet Haryo Pranoto

Manufacturing, Materials and Metallurgy, Advanced Metrology, Design and Simulation Universitas Muhammadiyah Kalimantan Timur (UMKT) Indonesia



Assoc. Prof. Dr. Supriyono Materials Engineering, Computational Solid Mechanics Universitas Muhammadiyah Surakarta (UMS) Indonesia







Assoc. Prof. Dr. Waluyo Adi Siswanto Computational Mechanics, Finite Element Analysis, Biomechanics Universitas Muhammadiyah Surakarta (UMS) Indonesia



Mr. Mohammed Hussien Rady

mechanical engineering Wasit University Iraq



Assoc. Prof. Dr Otsuka Yuichi Biomaterials, Material science Nagaoka University of Technology Japan



Dr. Abdul Latif Mohd Tobi Finite Element Analysis, Computational Mechanics, Fatigue & Fracture Universiti Tun Hussein Onn Malaysia (UTHM)

Malaysia

3/26/23, 10:15 AM



Synthesis of Polymer from Renewable materials Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia



Assoc. Prof. Ts. Dr. Hamimah Abd Rahman Advanced ceramics, solid oxide fuel cell, electrophoretic deposition, ceramic foan Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia



Assoc. Prof. Dr. Hariati Binti Mohd Taib Material science, Advance materials, Ceramics Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia

Assoc. Prof. Dr. Anika Zafiah Binti Mohd Rus



Assoc. Prof. Dr. Maizlinda Izwana Binti Idris Material Scienc, Composite materials Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia



Assoc. Prof. Dr. Mohammad Sukri Mustapa Structural Integrity, Fatigue Failure, Fatigue Crack Growth, Fracture Mechanics, Fibre Composite Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia



Dr. Mohammad Zulafif Rahim Materials Manufacturing, Advanced Machining, Machine Design Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia



Mr. Nagentrau Muniandy Mechanics of material, Finite element method, Hardfacing KDU University College Malaysia



Dr. Sharifah Adzila Binti Syed Abu Bakar Advanced materials, Biocompatible Materials, Biomaterials Universiti Tun Hussein Onn Malaysia (UTHM) Malaysia



Ts. Dr. Zakiah Binti Kamdi Material sciences, Advanced materials Universiti Tun Hussein Onn Malaysia (UTHM) **Malaysia**

٩

Dr Nguyen Hoc Thang Materials Engineering, Inorganic Chemical Engineering, Environmental Engineering Ho Chi Minh City University of Food Industry Vietnam

Organiser:

Master Mechanical Engineering Programme, School of Graduate Studies, Universitas Muhammadiyah Surakarta

In collaboration with:

- Bachelor Mechanical Engineering Programme, Faculty of Engineering, Universitas Muhammadiyah Surakarta

- Bachelor Mechanical Engineering Programme, Faculty of Science and Technology, Universitas Muhammadiyah Kalimantan Timur

- Asosiasi Program Studi Teknik Mesin Perguruan Tinggi Muhammadiyah

